

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application.

Please cancel claims 6 and 22-24 without prejudice.

Please amend claims 1, 2, 10, 11, 19 and 21 as indicated below (material to be inserted is in **bold and underline**, material to be deleted is in ~~strikeout~~ or (If the deletion is of five or fewer consecutive characters or would be difficult to see) in double brackets [[]]):

Listing of Claims:

1. (Currently Amended) A method of preparing a surface for adhesion, the method comprising:

providing an initiator **in the form of precursors of structures formed by ablation of a substrate** which is configured to shadow a portion of a surface of a **the** substrate;

directing a laser toward the surface of the substrate to effect ablation of a non-shadowed portion of the substrate, forming structures on the surface of the substrate; and

applying an adhesive to the surface of the substrate.

2. (Currently Amended) The method of claim 1, wherein providing an initiator includes ~~permitting~~ **resettling** ablation debris, which results from initial ablation of the surface of the substrate, ~~to-resettle~~ on the surface of the substrate where the ablation debris has a higher ablation threshold than the surface of the substrate.

Page 2 - AMENDMENT
Serial No. 10/052,815
HP Docket No. 10012053-1
KH Docket No. HPCC 321

3. (Original) The method of claim 1, wherein providing an initiator includes providing a substrate incorporating particles with an ablation threshold higher than an ablation threshold of the surface of the substrate.

4. (Original) The method of claim 3, wherein providing an initiator also includes determining the desired size, shape and density of structures and selecting an appropriate number of particles to form the desired density of structures.

5. (Original) The method of claim 1, wherein providing an initiator includes spreading particles on the surface of the substrate where the particles have an ablation threshold higher than an ablation threshold of the surface of the substrate.

6. (Cancelled)

7. (Original) The method of claim 1, wherein the substrate is formed from a liquid crystal polymer or a polyimide.

8. (Original) The method of claim 1, wherein the substrate is formed from a polyimide.

9. (Original) The method of claim 1, wherein the substrate is an element of a print cartridge assembly.

10. (Currently Amended) A method of preparing a surface for adhesion, the method comprising:

directing laser radiation towards the surface of the substrate to effect ablation of the substrate and create ablation debris, the ablation debris having a higher ablation threshold than the surface of the substrate;

permitting resettling the ablation debris to ~~resettle~~ on the substrate surface and to shadow a portion of the surface from laser radiation;

Page 3 - AMENDMENT
Serial No. 10/052,815
HP Docket No. 10012053-1
KH Docket No. HPCC 321

further directing laser radiation towards the surface of the substrate at an intensity sufficient to cause ablation of the substrate, but not sufficient to cause substantial ablation of the debris, thereby forming structures on the surface of the substrate.

11. (Currently Amended) The method of claim 10, ~~wherein providing an initiator includes providing~~ which further comprises, prior to directing laser radiation towards the substrate, providing an initiator configured to shadow a portion of the surface of the substrate.

12. (Original) The method of claim 11, wherein providing an initiator includes providing a substrate incorporating particles with an ablation threshold higher than an ablation threshold of the surface of the substrate.

13. (Original) The method of claim 11, wherein providing an initiator also includes determining the desired size, shape and density of structures and selecting an appropriate number of particles to form the desired density of structures.

14. (Original) The method of claim 11, wherein providing an initiator includes spreading particles on the surface of the substrate where the particles have an ablation threshold higher than an ablation threshold of the surface of the substrate.

15. (Original) The method of claim 10, wherein the substrate is formed from a liquid crystal polymer

16. (Original) The method of claim 10, wherein the substrate is formed from a polyimide.

17. (Original) The method of claim 10, wherein the substrate is an element of a print cartridge assembly.

18. (Original) A method of increasing adhesion of an adhesive to a substrate, the method comprising:

directing a laser at a surface of a substrate to cause ablation of the surface and formation of ablation debris;

adjusting the fluence of the laser between an ablation threshold of the substrate and an ablation threshold of the ablation debris;

ablating the surface of the substrate;

progressively covering the surface of the substrate with ablation debris to effect formation of raised structures on the surface of the substrate; and

applying an adhesive to the surface of the substrate.

19. (Currently Amended) The method of claim 18, wherein progressively covering the substrate with ablation debris includes ~~permitting~~ resetting the ablation debris ~~to-resettle~~ on the surface of the substrate such that a first portion of the surface is covered with ablation debris and a second portion of the surface is uncovered with ablation debris, and ablating the uncovered portion of the surface to form structures in the covered portion of the surface.

20. (Original) The method of claim 18, wherein the substrate is formed from a liquid crystal polymer.

21. (Currently Amended) A method of eliminating interfacial failure between a first component and an adhesive in a print cartridge assembly, the method comprising:

directing a laser at a surface of a first component;

shadowing a portion of the surface of the first component with precursors of structures formed by ablation of the surface of the first component to form a high threshold ablation region and a low threshold ablation region;

adjusting the laser to ablate the low threshold ablation region at a rate faster than ablation of the high threshold ablation region in order to form structures on the surface of the first component; and

applying an adhesive to the surface of the first component.

22. (Cancelled)

23. (Cancelled)

24. (Cancelled)

25. (Original) The method of claim 21, wherein the first component is a print cartridge body.

26. (Original) The method of claim 21, wherein the first component is a flex circuit.

27. (Cancelled)

28. (Cancelled)

29. (Cancelled)

30. (Cancelled)

31. (Cancelled)

32. (Cancelled)

33. (Previously Presented) The method of claim 1, wherein the structures formed on the surface of the substrate are approximately between two and five microns in height.

34. (Previously Presented) The method of claim 1, wherein the surface of the substrate is a surface of a print cartridge body.

35. (Previously Presented) The method of claim 1, wherein the surface of the substrate is a surface of a flex circuit.

36. (Previously Presented) The method of claim 10, wherein the structures formed on the surface of the substrate are approximately between two and five microns in height.